

PTFE CG25
TECHNICAL DATA SHEET



FULL NAME: POLYTETRAFLUOROETHYLENE FILLED 25% CARBON-GRAPHITE

PHISICAL – MECHANICAL PROPERTIES	METHOD	UNIT	MOULDED	EXTRUDED
DENSITY	ASTM D792	G/CM ³	-	2,04 – 2,10
HARDNESS – SHORE D	ASTM D2240	/	-	≥ 64
TENSILE STRENGTH – CD	ISO 12086 ISO 527	N/MM ²	-	≥ 12
ELONGATION AT BREAK – CD	ISO 12086 ISO 527	%	-	≥ 50

THERMAL PROPERTIES				
SERVICE TEMPERATURE (MIN – MAX)	/	°C	-	- 200 / +260
THERMAL EXPANSION COEFFICIENT (LINEAR) 25 – 100°C	SIMILAR TO ASTM D696	10 ⁻⁵ (MM/MM)/°C	-	10 - 12

ELECTRICAL PROPERTIES				
VOLUME RESISTIVITY	ASTM D257	Ω • CM	-	10 ³
SURFACE RESISTIVITY	ASTM D257	Ω	-	10 ³

REV.	DATE	DESCRIPTION	MODIFIED PARAGRAPHS	WRITTEN BY	APPROVED BY
01	12/2020	LAYOUT UPDATE	//	601.203	601.203

THIS DATASHEET AND ALL PROPRIETIES INDICATED COME DIRECTLY FROM THE PRODUCER'S STUDIES AND TESTS. D.H. LAMINA S.R.L. DOES NOT PRODUCE THE MATERIAL.
THE CONTENTS OF THIS DATASHEETS ARE MEANT TO GIVE AN OVERVIEW OF THE PRODUCT'S PROPRIETIES. IT REFLECTS OUR CURRENT KNOWLEDGE AND MAY NOT BE COMPLETE. THE VALUES SHOULD BE TAKEN AS GUIDE VALUES BECAUSE THEY ARE DEPENDENT ON SURROUNDING CONDITIONS AND MACHINING METHODS. THE VALUES ARE IN NO WAY A LEGALLY BINDING ASSURANCE OF THE PRODUCT'S PROPRIETIES OR ITS SUITABILITY FOR USE IN A SPECIFIC APPLICATION. ALL STATED VALUES ARE AVERAGE ESTABLISHED FROM MANY INDIVIDUAL TESTS. FOR SPECIFIC APPLICATIONS, WE RECOMMEND DETERMINING SUITABILITY BY MEANS A TRIAL.

D.H. LAMINA S.R.L.

Via Santellone, 29/A • 25080 Molinetto di Mazzano (BS) • Italy
Tel. +39 (0) 30 21 20 448 • Fax +39 (0) 26 20 813
Capitale Sociale € 46.800,00 Interamente versato
C.F. e Nr. Iscr. Registro Imprese 01685670174
P.I. IT01685670174 • REA BS-262362
PEC: dhlamina@pec.it • dhlamina@dhlamina.it • www.dhlamina.it